

gloveon Ridley



Latex Exam Gloves Powder Free, Standard Cuff

Our **Ridley** latex exam glove is named after the rubber pioneer, Sir Henry Ridley (1855-1956). Just like this pioneer, our Ridley gloves have also conquered many different market segments due to its versatile features. It has a proven unquantifiable aqueous latex proteins reading, and its non-sensitising & non-irritant properties continues to be the most popular choice of powder free latex glove in our range.



GloveOn Ridley		
Length (mm)	≥ 230	
Thickness Measurements (mm)		
Palm (centre of Palm)	0.13 ± 0.03	
Finger (13mm ± 3mm from tip)	0.14 ± 0.03	
Physical Properties	Before Ageing	After Ageing
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 650	≥ 500
Inspection Levels & AQL	Inspection Level	AQL
Watertightness	G1	1.50
Physical Dimensions	S2	4.00
Tensile Strength	S2	4.00
Visual Inspection (Major)	S4	2.50
Visual Inspection (Minor)	S4	4.00
Particulate Residue	N = 5	≤ 2mg/glove
Protein Content	N = 3	≤ 50µg/g

REORDER CODE

CHL11XS	X-SMALL
CHL11SS	SMALL
CHL11MM	MEDIUM
CHL11LL	LARGE
CHL11XL	X-LARGE

FEATURES

- Fully textured
- Powder free
- Made with natural rubber latex
- Protein level ≤ 50µg/g
- Ambidextrous
- Standard cuff
- Natural colour

PACKAGING

100 gloves per box for XS to XL
10 boxes per carton

REGULATORY COMPLIANCE

TGA - ARTG 127794, FDA 510(k), REACH, EC 10/2011, REGULATION (EC) No 1935/2004, EC 1935/2004, CMDR SOR-98-282

STANDARDS

ASTM D3578, EN 455 part 1, 2, 3 & 4, EN 1186, EN 13130, CEN/TS 14234, ISO 11193 - 1, AS/NZS 4011:1997

MANUFACTURING ACCREDITATIONS

ISO 9001:2008
ISO 13485:2003
EN ISO 13485:2003

*Full test reports on Sensitisation Testing, Primary Skin Irritation and Residual Proteins Testing are available upon request.

A brand by



Mun Australia
Toll free: 1800 456 837 (GLOVES)
info.au@munglobal.com



Protection Always On