

gloveon Paladin



Nitrile Exam Gloves Powder Free, Long Cuff

This customised long cuff nitrile glove at almost 5mil thick is ideal for job that demands extra tensile strength and additional cuff length. It is used extensively by medical profession, laboratory, manufacturing and by the shining knights of the emergency and rescue services.



GloveOn Paladin		
Length (mm)	≥ 280	
Thickness Measurements (mm)		
Palm (centre of Palm)	0.10 ± 0.02	
Finger (13mm ± 3mm from tip)	0.13 ± 0.02	
Physical Properties	Before Ageing	After Ageing
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 500	≥ 400
Inspection Levels & AQL	Inspection Level	AQL
Watertightness	G1	1.50
Physical Dimensions	S2	4.00
Tensile Strength	S2	4.00
Visual Inspection (Major)	S4	2.50
Visual Inspection (Minor)	S4	4.00
Particulate Residue	N = 5	≤ 2mg/glove

REORDER CODE

NTR36XS	X-SMALL
NTR36SS	SMALL
NTR36MM	MEDIUM
NTR36LL	LARGE
NTR36XL	X-LARGE
NTR36XXL	XX-LARGE
NTR36XXXL	XXX-LARGE

FEATURES

- Fingertip textured
- Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested
- Ambidextrous
- Long cuff
- Cobalt blue colour

PACKAGING

100 gloves per box for XS to 3XL
10 boxes per carton

REGULATORY COMPLIANCE

TGA - ARTG 164563, FDA 510(k),
MDD 93/42/EEC, REACH,
ROHS Directive 2002/95/EC

STANDARDS

ASTM D6319, ASTM 6978,
EN455 part 1, 2, 3 & 4, ISO 11193 - 1,
AS/NZS 4011:1997

MANUFACTURING ACCREDITATIONS

ISO 9001:2008
ISO 13485:2003
EN ISO 13485:2012

Chemotherapy Drugs and Concentration
(Tested for Resistance to Permeation by Chemotherapy
Drugs as per ASTM D6978-05-Test Report PN 101115B)

Minimum Breakthrough
Detection Time (minutes)

Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	30.1 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.0mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	57 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

WARNING: Carmustine and Thiotepa, at the tested concentration, degraded Paladin nitrile glove at 30.1 minutes and 57 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

A brand by

mung
www.munglobal.com

Mun Australia
Toll free: 1800 456 837 (GLOVES)
info.au@munglobal.com

**Birthing Kit
Foundation**
Australia
Proud Supporter of
Birthing Kit Foundation (Australia)

gn Protection Always On